

data sheet

specialist | woodstain TP



technical specifications

| | |
|----------------------------|--|
| % volume solids | approximately 31% |
| density | approx. 1,0gr/dm ³ |
| viscosity | approx. 2,5d'Pas |
| gloss | matt |
| drying | dust free approximately 1 hours recoatable approximately 4 hours |
| storage | cool and frost-proof, the quality of the product should not deteriorate during storage |
| thinner | water |
| elasticity | very good |
| application | brush, roller, spray (cup) for horizontal treatment |
| shelf life | a minimal shelf life of 12 months when kept in an unopened tin |
| cleaning of equipments | warm water |
| application conditions | min. 8°C ambient and surface temperature and relative humidity max. 85% |
| composition | binder: a combination of pu and modified alkyd emulsion |
| theoretical spreading rate | woodstain TP has a theoretical spreading rate at 25 micron dry: approx. 12m ² /litre |
| special note | for more information regarding our specialist transparent woodstains please refer to the corresponding safety data sheet |



product code | 17-0219

principal characteristics good outdoor durability
good penetration in first coat wood,
micro porous, low film-build, good resistance to uv radiation,
easy to apply, good adhesion on bare wood, translucent
(enhances the woods texture)

use as one-pot system or as a impregnating primer in
water-borne translucent systems for all kinds of woods

colour(s) standard translucent wood colours