

data sheet

modifica QD | opaque topcoat



technical specifications

% volume solids	approx. 36%
density	approx. 1,1 kg/dm ³
thinner	undiluted, if any, water
gloss	semi-matt (40-45 GU 60°C)
drying	dust free approximately 1 hour tack free approximately 2 hours recoatable approximately 4-5 hours
storage	cool and frost-proof, the quality of the product should not deteriorate during the storage.
flow	sufficient
application	airless or airmix
application data	apply 2 layers of 400 Mu (wet) Course and rough suraces needed higher thickness to be effectively sealed
cleaning of equipment	water
application conditions	min. 8°C ambient and surface temperature and relative humidity max 85%
shelf life	minimal 12 months in when kept in an unopened tin for more information, see the safety data sheet of this product
theoretical spreading rate at 200 microns dry	at 50 microns dry: approx. 7 m ² /litre Storage



product code	17-0735
composition	special modifies self crosslinking acrylic polymer
principal characteristics	<ul style="list-style-type: none"> - good outdoor durability - fast drying - good weather resistance - non yellowing - good UV protection - excellent smooth Finish
use	dimensionally stable wooden components, limited dimensionally stable wooden parts
colour(s)	all colors available including colourmatching