

# data sheet

exterior | end grain sealer



## technical specifications

% volume solids	approximately 50%
deposit	approximately 1, 2-1, 3 (white)
viscosity	20-30poises (dPa.s)
gloss	eggshell
drying	dust free   approximately 1 hour tack free   approximately 2 hours handling   approximately 3 hours recoatable   approximately 3 hours
filling	good
flow	sufficient
application	brush
application data	apply 2 layers of 400 Mu (wet). Course and rough suraces needed higher thickness to be effectively sealed.
cleaning of equipments	(hot) water
application conditions	do not use 5°C and a maximum relative humidity of 85%
shelf life	6 month ex-works; product should be stored indoors in the original unopened and undamaged packed in a dry/ cool place.
theoretical spreading rate at 200 microns dry	Exterior End Grain Sealer has an approximate theoretical spreading rate of 4m <sup>2</sup> /litre
safety aspects	see information on safety data sheet
transport information	see information on safety data sheet



product code | 25-0350

composition	special polymers and reinforced powders
principal characteristics	quick drying/handling, high build, high layer thickness without sagging, high impact resistance, high water resistance, good adhesion, recoatable 1k waterbased and solventbased paints
use	suitable for sealing wood edges of window frames and plywood materials
colour(s)	white and transparent