



Transparent Topcoat (Semi-Gloss)

Data Sheet



Product Code: 17-0659	:	water-borne transparent satin gloss primer, mid and final coating for exterior and interior wooden components, for industrial application on front joinery.
Composition indication	:	binder : alkyd resin emulsion
Principal characteristics	:	<ul style="list-style-type: none">- good UV protection- good outdoor durability- fast drying- good weather resistance- good blocking resistance- deep penetration- one-pot system
Use	:	dimensionally stable wooden components, limited dimensionally stable wooden parts.
Color	:	transparent colors

Technical specifications (20°C and 55% R.H.)

% volume solid	:	approx. 40%
Density	:	approx. 1,2
Gloss	:	satin gloss (25-30 GU 60°C)
Drying	:	<ul style="list-style-type: none">- dustdry : approx. 1 hour- recoatable : approx. 4 hours
Application	:	airless of airmix spraying (applicable up to 300 microns wet layer thickness)
Thinner	:	undiluted, if any, water
Cleaning tools	:	water



Transparent Topcoat (Semi-Gloss)

Data Sheet

Spraying data	:	<u>airless</u>	
	- pressure		: approx. 100-150 bar
	- nozzle		: 0,011-0,013 inch
		<u>airmix</u>	
	- pressure		: approx. 1 bar airpressure
Application temperature	:	min. 8°C ambient and surface temperature and relative humidity max. 85%.	
Theoretical spreading rate	:	at 50 microns dry film thickness: 8 m ² /liter	
Storage	:	cool and frost-proof, the quality of the product should not deteriorate during the storage.	
Shelf life	:	minimal 6 months in unopened tin.	
Special note	:	for more information, see the safety data sheet of this product.	

Disclaimer

The information given in this technical data sheet is only a general product description, based on our experiences and tests and therefore does not represent a specific practical case. Consequently Anker Stuy Verven doesn't guarantee the functionality or result and takes no responsibility in this respect. We advise our clients to test the applicability of the product to the nature and the state of the surfaces and to carry out the necessary representative tests in case of doubt. Please contact our R&D department as the occasion arises. Attention: our clients should verify whether the present technical data sheet hasn't been replaced by a more recent version.