















16-0266 Ankertros Acryl PU Lak

Versie 160229 : high quality, non yellowing clear satin gloss varnish on

the basis of a specific urethane acrylic technology.

Composition : binder : special modified

waterborne urethane-

acrylic

Principal characteristics : - good blocking resistance

odourlessfast drying

- very well scratch and abrasion resistant

- less environment polluting

good flow

Use : interior, as an abrasion resistant finish of wood. For

stairs, furniture, boarding etc.

Color : colorless

Technical Specifications (20°C and 55% R.H.)

Solids content : approx. 35%

Density : approx. 1,03 gr/cm³ (white)

Viscosity : approx. 120 sec. DC4

Gloss : available in satin, halfmatt and naturel matt

Drying time : - dust-dry : approx. 1 hour

- recoatable : approx. 3-4 hours

Application : brush, roller, spray

Thinner : ready to use, do not dilute

Cleaning tools : water

Application temperature : min. 18°C ambient and surface temperature and

relative humidity max. 85%.



Anker Stuy Verven BV | Hellingwal 1 | 8407 EM Terwispel | Tel. +31 (0)513 465 000 | info@ankerstuy.nl | www.ankerstuy.nl

Theoretical spreading rate : at 30 micron dry: approx. $10 \text{ m}^2/\text{l}$.

Storage : cool and frost-proof.

Shelf life : minimal 6 months in unopened tin.

Special note : for more information, see the safety data sheet of this

product.

Disclaimer

The information given in this technical data sheet is only a general product description, based on our experiences and tests and therefore does not represent a specific practical case. Consequently Anker Stuy Verven doesn't guarantee the functionality or result and takes no responsibility in this respect. We advise our clients to test the applicability of the product to the nature and the state of the surfaces and to carry out the necessary representative tests in case of doubt. Please contact our R&D department as the occasion arises. Attention: our clients should verify whether the present technical data sheet hasn't been replaced by a more recent version.



Anker Stuy Verven BV | Hellingwal 1 | 8407 EM Terwispel | Tel. +31 (0)513 465 000 | info@ankerstuy.nl | www.ankerstuy.nl